

ARMY RESEARCH LABORATORY



Parametric Erosion Investigation (Propellant Adiabatic Flame Temperature)

by Paul J. Conroy, Paul Weinacht,
and Michael J. Nusca

ARL-TR-1954

June 1999

19990623 041

Approved for public release; distribution is unlimited.

DTIC QUALITY INSPECTED 4

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

Army Research Laboratory

Aberdeen Proving Ground, MD 21005-5066

ARL-TR-1954

June 1999

Parametric Erosion Investigation (Propellant Adiabatic Flame Temperature)

Paul J. Conroy, Paul Weinacht, and Michael J. Nusca
Weapons and Materials Research Directorate, ARL

Approved for public release; distribution is unlimited.

Abstract

In this report, we investigate the influence of quasi-independent parameters and their potential influence on erosion in guns. Specifically, we examine the effects of flame temperature and the effect of assuming that the Lewis Number (ratio of mass to heat transport to the surface), Le , is one. The adiabatic flame temperature was reduced for a propellant through the addition of a diluent from a high of 3,843 K similar to that of M9 down to 3,004 K, which is near the value for M30A1 propellant. Mass fractions of critical species at the surface with and without the assumption of $Le = 1$ are presented, demonstrating that certain species preferentially reach the surface providing varied conditions for the surface reactions. The results for gun tube bore surface regression qualitatively agree with previous studies and with current experimental data. The propellant composition influence upon erosion must still be inferred at this time from the presence of specific product species at the surface because the finite-rate gas surface reactions are not well known under ballistic conditions.

Table of Contents

	<u>Page</u>
List of Figures	v
List of Tables	vii
1. Introduction	1
2. Erosion Model Description	1
3. Calculation Methodology for Flame-Temperature Study	4
4. Results	6
5. Conclusions	14
6. References	15
Distribution List	17
Report Documentation Page	27

INTENTIONALLY LEFT BLANK.

List of Figures

<u>Figure</u>	<u>Page</u>
1. Conceptual Erosion Model Illustration	3
2. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,843 K	7
3. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,603 K	7
4. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,384 K	8
5. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,004 K	8
6. Computed Single-Shot Erosion Depths vs. Time for Propellant Flame Temperatures of 3,843 K; 3,603 K; and 3,384 K at Three Axial Locations Each ..	9
7. Computed and Experimental Normalized Erosion per Round vs. Adiabatic Flame Temperature	10
8. 155-mm Howitzer Origin of Rifling Showing Pyrolysis, Loss of Chrome, and Rifling Degradation	11
9. 120-mm M256 Tank Cannon Surface at Forcing Cone Showing Chrome Stripping, Pits, and Melt Regions	12
10. Selected Product Species Mole Fractions and the CO/CO ₂ Ratio for the Gun Tube Core Flow	13
11. Selected Product Species Mole Fractions and the CO/CO ₂ Ratio for the Gun Tube Surface	14

INTENTIONALLY LEFT BLANK.

List of Tables

<u>Table</u>	<u>Page</u>
1. Calculation Matrix to Investigate the Effect of Flame Temperature	5

INTENTIONALLY LEFT BLANK.

1. Introduction

The inner surfaces of most gun tubes regress as a result of various mechanisms, such as mechanical abrasion, pyrolysis, melting, spalling, and possibly others, when the gun is fired. Historically, the propellant adiabatic flame temperature (obtained from Gibbs free energy minimization with constant volume and no heat loss) has been considered to be the most important factor in determining erosivity [1–3]. Previous modeling and experimental efforts have not identified the fundamental cause of the erosion, and some discrepancies were found between flame-temperature correlations [3–5]; the discrepancies were not resolved. Attempts to model erosion using first principles have been and are currently being made [6–9], although it is believed that significant additional work is still required to understand the fundamental physics involved.

In this study, the influence of propellant flame temperature on erosion is analyzed as an initial step toward understanding the principle components of the erosion problem in a parametric fashion. The contributions due to mechanical wear and abrasion are not included in the study, nor are the effects of altered material composition on the surface. Instead, this study focuses on the surface thermochemical portion of erosion using full equilibrium thermochemistry, independent heat transport, and multicomponent species mass transport to the surface.

2. Erosion Model Description

Although described elsewhere [8, 9], for completeness, the basic outline and new additions to the U. S. Army Research Laboratory (ARL) erosion physics test model are elaborated upon here. The model consists of three fully coupled portions consisting of thermal ablation/heat transfer/conduction, mass transport, and thermochemistry. The code uses the gas-phase properties in the core flow of the gun tube from XKTC [10], and certain data from IBBLAKE [11–13]. The thermochemistry is assumed to be full-equilibrium chemistry and incorporates the NASA LEWIS [14] database. New additions to the model include:

- (1) variable surface physical properties, conductivity $k(T)$, and specific heat $C_p(T)$;
- (2) surface material phase change from body-centered cubic (BCC) to face-centered cubic (FCC) (the material replenishment section recognizes the surface temperature and the correct phase);
- (3) a user-defined “freeze-out” temperature that deactivates the surface chemistry;
- (4) an iterative procedure that provides convergence for surface-control volume temperature (the gas and solid specific heats are temperature-dependant and require iteration for convergence); and
- (5) all user-defined primary inputs (i.e., no hardwired inputs and case to case consistency).

The model considers both melting and pyrolysis from surface chemistry. Conceptually, as shown in Figure 1, the surface heats from convection until the chemical activation temperature is overcome. At this point, surface reactions are permitted to occur, releasing additional energy into the system as a source term at the surface and producing appropriate gaseous, solid, or liquid products. The reaction products can be either remain as some solid materials or be removed from the area as liquids or gases. The later case results in pyrolysis or ablation. As the surface regresses, the solids are refreshed accordingly.

The following assumptions have been made in the erosion model:

- (1) one-dimensional (1-D) heat conduction,
- (2) no subsurface chemical diffusion or reactions,
- (3) instantaneous removal of all surface liquids and gas products,




Figure 1. Conceptual Erosion Model Illustration.

- (4) no feedback to the interior ballistics calculation in the core flow,
- (5) release and treatment of chemical energy as a surface source term, and
- (6) freezing of species (i.e., no chemical reactions) from the core flow to the wall.

The surface energy balance (when there is no melting) consists of the convective heat input to the surface, along with the possible contribution due to the surface reaction, shown in equation (1), where T is the wall temperature, k is the thermal conductivity, and h is the convection coefficient [15]. This source term is balanced with the energy conducted through the material:

$$h(T_{\text{gas}} - T_{\text{wall}}) = -k \frac{\partial T}{\partial r} - \text{Source}. \quad (1)$$

However, when the system is melting, the energy balance also includes the fixed-surface temperature condition (because the temperature cannot rise beyond this value as the material is removed as fast

as it melts and additional energy is preferentially used for more phase transition), as well as the latent heat of formation of the molten material, as shown in equations (2) and (3):

$$T_{\text{wall}} = T_{\text{melt}} , \quad (2)$$

and

$$\rho L \frac{\partial s}{\partial t} = h (T_{\text{gas}} - T_{\text{wall}}) + k \frac{\partial T}{\partial r} + \text{Source} . \quad (3)$$

In equation (3), L is the latent heat of formation, ρ is the density of the surface material, and s represents the instantaneous surface location that must be iterated upon for convergence until the energy balance is satisfied.

3. Calculation Methodology for Flame-Temperature Study

The calculations presented in this study were initiated with a BLAKE calculation of a notional propellant having an adiabatic flame temperature of 3,843 k. This particular baseline propellant (an altered JA2) was chosen because it had an exceptionally high adiabatic flame temperature, as well as it previously experimentally demonstrated erosivity [9]. The basic charge configuration had a notional slab geometry. The propellant flame temperature was reduced from the nominal value by adding a diluent (N_2) to the nominal gas mixture in increasing mass percentages of 15%, 30%, and 60%, without reducing the other components' mass fractions. As a result, the final percentage of diluent added was somewhat less than stated previously, as shown in Table 1.

Using these formulations for the propellants with reduced flame temperature, ranging from 3,843 K down to 3,004 K, iterations were then performed for the XKTC calculations, which involved altering the propellant mass and web, such that the projectile muzzle velocity, muzzle energy, and the peak pressure in the gun were held constant for all four scenarios. The results were used in the IBBLAKE calculations. These calculations involved many iterations in order to determine the

Table 1. Calculation Matrix to Investigate the Effect of Flame Temperature

M256 ^a With a 3.629-kg Projectile (% N ₂)	Muzzle Velocity (m/s)	Peak Pressure (MPa)	Propellant Mass (kg)	Mole (% Carbon)	Mole (% Hydrogen)	Mole (% Oxygen)	Mole (% Nitrogen)	Adiabatic Flame Temperature (K)
RPD 351 Nominal	1537.0	453.0	6.074	19.694	27.406	40.794	11.932	3,843
+15	1544.1	451.9	6.346	17.634	24.539	36.526	21.145	3,603
+30	1542.2	453.4	6.623	15.964	22.215	33.067	28.613	3,384
+60	1538.9	456.7	8.165	13.422	18.677	27.801	39.981	3,004

^a Assumed nonchromium electroplated M256 tank cannon.

combination of projectile mass, propellant mass, and web size which produced the desired results, while maintaining a burn-out condition at projectile exit. Although the total charge mass is changed for each permutation (see Table 1) an attempt is made to account for this effect later when presenting the results.

The resulting information involving the gun tube core flow gas composition, temperature, pressure, and velocity for the four different scenarios was then used as input for the calculations; the results of which are discussed in section 4.

4. Results

Shown in Figures 2–5 are gun tube, inner-surface temperatures for three of the four notional propellant formulations (Table 1) at three axial locations along the gun tube wall, measured from the rear face of the tube: 635 mm; 686 mm; and 1,040 mm. The initial location of the base of the projectile is 559 mm. The flat areas at the top of the curves in Figures 2–4 are due to the surface temperature reaching a user-defined, surface melt temperature. What is seen in this data is the general reduction from the high, overall temperatures in Figure 2 to the lower temperatures in Figure 5. Note that Figures 2–4 reflect the time at which the surface remains at the melt temperature. Therefore, the larger these regions are, the more time the surface remained at the melt temperature and, thus, the more material was removed. However, for the propellant with the lowest adiabatic flame temperature of 3,004 K, the gun tube, inner-surface temperatures do not reach the melting temperature at any axial location in Figure 5, while, for the charge containing the propellant with the adiabatic flame temperature of 3,384 K (shown in Figure 4), only one axial location reaches the melting temperature. The two higher adiabatic flame temperature of 3,843 K and 3,603 K exhibit melting at two of the three chosen axial locations in Figures 2 and 3.

Figure 6 integrates the total mass loss over time for the three propellants with the higher flame temperatures. The slight increase in the recession in Figure 6 before 3.5 ms and after 4.5 ms in the curves is due to the pyrolysis, which is also included in the total mass loss and intended for a follow-on study.




Figure 2. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,843 K.




Figure 3. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,603 K.




Figure 4. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,384 K.




Figure 5. Gun Tube Surface Temperatures for Three Axial Locations and a Single Firing of a Charge Having a Propellant Adiabatic Flame Temperature of 3,004 K.




Figure 6. Computed Single-Shot Erosion Depths vs. Time for Propellant Flame Temperatures of 3,843 K; 3,603 K; and 3,384 K at Three Axial Locations Each.

In Figure 7, both experimental and numerical data are presented as normalized erosion (surface regression) vs. adiabatic flame temperature. The experimental data include some data from a study presented by Ahmad [16] concerning 5-in/54 gun tube erosion data, as well as Kruczynski's [17] M199 M203A1 origin of rifling wear data per round and the original version of the M919 25-mm-round average wear per round at the origin of rifling [18]. Ahmad's data include two different experimental data sets for a 5-in/54 system. The values with higher erosion are for a series of firings without coolant additives in the charge, while a series presented with lower erosive values included a talc wax liner in the charges to reduce the overall heat transported to the gun tube wall. Kruczynski's data include both horizontal and vertical wear at the origin of rifling to account for the asymmetrical wear pattern seen in some artillery charges; however, both points are practically coincidental for this plot, including values not shown for the M203 charge.




Figure 7. Computed and Experimental Normalized Erosion per Round vs. Adiabatic Flame Temperature. The Numerical Calculations Are Also Normalized for Charge Mass Effects. The Adiabatic Flame Temperature for Various Propellants Is Shown for Reference.

The computed numerical data shown in Figure 7 consist of two curves of four points each and are plotted as triangles. Both curves have been normalized to the maximum amount of computed wear occurring at the 635-mm axial location. The lower of the two curves reflects this normalization by having 1.0 as the maximum value of regression. This computed data was then renormalized to incorporate the maximum charge mass, as well as the maximum surface regression (percent maximum erosion/percent maximum charge), which resulted in the slightly higher plot. The general trend and values of erosivity vs. adiabatic flame temperature seems to be reasonable when compared to the experimental data presented for the 155-mm and 25-mm guns, which has also been normalized for regression.

While the general regression trend and shape holds for the data of Ahmad [16], the values appear to be inexplicably shifted in temperature by about 700 K, possibly due to the fact the Ahmad was firing experimental charges. An interesting note in Figure 7 is that, even though no melting occurred for the propellant having the adiabatic flame temperature very close to that of M30A1, the computed

surface regression was about that seen by Kruczynski [17] who was firing M30A1 propellant. These pyrolyzation products and related effects, as was stated, are an area of a follow-on study that will investigate the products that the equilibrium chemistry calculation indicates and what actually is being removed from the surface.

The photo of a 155-mm-howitzer origin of rifling in Figure 8 shows what type of erosion or pyrolyzation can occur at the origin of rifling. This photograph shows evidence of heat checking, cracking, and loss of lands; however, there is no obvious evidence of surface melting of this scale as the calculations predicted. Nonetheless, the situation is quite different for the M256 chromed gun tube shown in Figure 9, which fired JA2-type propellants. Evidence of chrome removal, surface pitting, and melting are all present in this photograph, as was also expected from the calculations.




Figure 8. 155-mm Howitzer Origin of Rifling Showing Pyrolysis, Loss of Chrome, and Rifling Degradation [17].




Figure 9. 120-mm M256 Tank Cannon Surface at Forcing Cone Showing Chrome Stripping, Pits, and Melt Regions [25].

Propellant combustion, product species, and molar concentrations are presented in Figures 10 and 11. The differences between the core flow product species in Figure 10 and the wall surface product species in Figure 11 are illustrative of the effect of multicomponent mass transport upon the species concentration at the surface. The species principally affected using nominal propellant by the mass transport are CO and CO₂. The concentrations in the core flow appear to contain less CO and more CO₂ than at the wall, where the concentration of CO rises and that of CO₂ is less. The CO/CO₂ varies approximately 15% between these regions. This ratio is thought to be very important [1, 19–24]. Fundamental studies are underway to investigate mechanisms in which free carbon may




Figure 10. Selected Product Species Mole Fractions and the CO/CO₂ Ratio for the Gun Tube Core Flow.




Figure 11. Selected Product Species Mole Fractions and the CO/CO₂ Ratio for the Gun Tube Surface.

be formed from either CO or CO₂ [24]. Eventually, the primary surface reactions and rates will be known and included in the surface reaction models. The proper state and species concentrations will be required to provide results based on experimentally validated physical processes.

5. Conclusions

Flame-temperature effects on erosion have been studied with four notional computational charges with the assumed gun tube properties for an M256 nonelectroplated cannon. These four notional charges had propellant adiabatic flame temperatures of 3,843 K; 3,603 K; 3,384 K; and 3,004 K. While the trends in erosion match those seen previously of Ahmad, the actual values agree better with recent system data, specifically, recently measured data from the 155-mm M203A1 charge and 25-mm M919 round erosion.

Differences in species concentrations exist between the core flow and wall region. This difference may be critical in providing the correct input for chemical reactions at the surface, but, as of yet, the actual mechanisms of erosion at the surface remain unknown.

Further parametric investigations of this type are needed in order to provide an understanding of the interactions of the thermal and chemical, with the ultimate inclusion of mechanical, components as well to erosion/wear. Also, this type of investigation provides guidance for further fundamental studies.

6. References

1. Fisher, E. B. "Heating and Wear Environment." *Proceedings of the U.S. Army Research Laboratory Sagamore Workshop on Gun Tube Heating and Erosion*, July 1996.
2. Caveny, L. H. "Steel Erosion Produced by Double Base, Triple Base, and RDX Composite Propellants of Various Flame Temperatures." ARLCB-CR-80016, U.S. Army Armament Research and Development Center, October 1980.
3. Lawton, B. "Thermal and Chemical Effects on Gun Barrel Wear." *Proceedings of the 8th International Symposium on Ballistics*, vol. 2, pp. 27-36, Orlando, FL, October 1984.
4. Watervliet Arsenal. *Proceedings of the Interservice Technical Meeting on: Gun Tube Erosion and Control*. Watervliet, NY, 25-26 February 1970.
5. U.S. Army Armament Research and Development Center. *Proceedings of the Tri-Service Gun Tube Wear and Erosion Symposium*. Dover, NJ, March 1977.
6. Evans, M. R. "User's Manual for Transient Boundary Layer Integral Matrix Procedure TBLIMP." Aerotherm UM-74-55, October 1974.
7. Dunn, S., D. Coates, G. Nickerson, S. Sopok, P. O'Hara, and G. A. Pflegl. "Unified Computer Model for Predicting Thermochemical Erosion in Gun Barrels." AIAA 95-2440, *Proceedings of 31st AIAA/ASME/SAE/ASEE Joint Propulsion Conference and Exhibit*, July 1995.
8. Weinacht, P., and P. J. Conroy. "A Numerical Method for Predicting Thermal Erosion in Gun Tubes." ARL-TR-1156, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, July 1996.
9. Conroy, P. J., P. Weinacht, and M. J. Nusca. "Surface Chemistry Effects on High Performance Tank Ammunition." ARL-TR-1526, U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, October 1997.
10. Gough, P. S. "The XNOVAKTC Code." BRL-CR-627, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, February 1990.
11. Freedman, E. "BLAKE - A Thermodynamic Code Based on Tiger: Users' Guide and Manual." ARBRL-TR-02411, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, July 1982.
12. Anderson, R. D., and K. D. Fickie. "IBHVG2 - A Users Guide." BRL-TR-2829, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, July 1987.

13. Janke, P. J., J. A. Dyvik, and C. L. Marksberry. "Electrothermo-Chemical Propellant Extensions to the IBHVG2 Interior Ballistics Simulation: Model Development and Validation." CPIA Publication 620, vol. 3, pp. 171–181, October 1994.
14. Gordon, S., and B. J. McBride. "Computer Program for Calculation of Complex Chemical Equilibrium Compositions, Rocket Performance, Incident and Reflected Shocks, and Chapman-Jouget Detonations." NASA SP-273, NASA LEWIS, OH, 1971.
15. Conroy, P. J. "Gun Tube Heating." BRL-TR-3300, U. S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, December 1991.
16. Ahmad, I. "The Problem of Gun Barrel Erosion: An Overview." *Gun Propulsion Technology*, vol. 109, chap. 10, 1988.
17. Kruczynski, D. L., I. C. Stobie, and M. B. Kummerich. "Gun Tube/Charge/Projectile Interactions and Gun Tube Wear." BRL-TR 3004, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, June 1989.
18. Talley, J. Q., and J. A. Owczarczak. "25-mm Barrel Erosivity Study." Final Report Prepared for GenCorp Aerojet Corporation, Aerojet Ordnance Division, Downey, CA, August 1991.
19. Kamdar, M. H., and J. D. Venables. "Characterization of Surface Layers in Gun Barrels." ARLCB-TR-84041, U.S. Army Armament Research and Development Center, Watervliet, NY 1984.
20. Morphy, C. C., and E. B. Fisher. "The Role of Carburization in Gun Barrel Erosion and Cracking." ARBRL-CR-00459, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, July 1981.
21. Morphy, C. C., and E. B. Fisher. "Gas Chemistry Effects on Gun Barrel Erosion: a Shock Tube Investigation." ARBRL-CR-00481, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD, June 1982.
22. Ringers, D. A., and J. B. Danese, Jr. "Quantum Chemistry, Chemisorption, and Erosion I. Properties of Diatomic Molecules." BRL-TR-2023, U. S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD 1977.
23. Weigand, J. H. "The Application of Erosion in Vent Plugs to Recoiless Guns." BRL-MR-340, U.S. Army Ballistic Research Laboratory, Aberdeen Proving Ground, MD 1945.
24. Chabalowski, C. Personal communication. U. S. Army Research Laboratory, Aberdeen Proving Ground, MD 1997.
25. Bundy, M. Personal communication. U.S. Army Research Laboratory, Aberdeen Proving Ground, MD, 1993.

NO. OF
COPIES ORGANIZATION

2 DEFENSE TECHNICAL
INFORMATION CENTER
DTIC DDA
8725 JOHN J KINGMAN RD
STE 0944
FT BELVOIR VA 22060-6218

1 HQDA
DAMO FDQ
D SCHMIDT
400 ARMY PENTAGON
WASHINGTON DC 20310-0460

1 OSD
OUSD(A&T)/ODDDR&E(R)
R J TREW
THE PENTAGON
WASHINGTON DC 20301-7100

1 DPTY CG FOR RDE HQ
US ARMY MATERIEL CMD
AMCRD
MG CALDWELL
5001 EISENHOWER AVE
ALEXANDRIA VA 22333-0001

1 INST FOR ADVNCD TCHNLGY
THE UNIV OF TEXAS AT AUSTIN
PO BOX 202797
AUSTIN TX 78720-2797

1 DARPA
B KASPAR
3701 N FAIRFAX DR
ARLINGTON VA 22203-1714

1 NAVAL SURFACE WARFARE CTR
CODE B07 J PENNELLA
17320 DAHLGREN RD
BLDG 1470 RM 1101
DAHLGREN VA 22448-5100

1 US MILITARY ACADEMY
MATH SCI CTR OF EXCELLENCE
DEPT OF MATHEMATICAL SCI
MAJ M D PHILLIPS
THAYER HALL
WEST POINT NY 10996-1786

NO. OF
COPIES ORGANIZATION

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL DD
J J ROCCHIO
2800 POWDER MILL RD
ADELPHI MD 20783-1145

1 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CS AS (RECORDS MGMT)
2800 POWDER MILL RD
ADELPHI MD 20783-1145

3 DIRECTOR
US ARMY RESEARCH LAB
AMSRL CI LL
2800 POWDER MILL RD
ADELPHI MD 20783-1145

ABERDEEN PROVING GROUND

4 DIR USARL
AMSRL CI LP (305)

NO. OF
COPIES ORGANIZATION

1 HQDA
SARD TR MS K KOMINOS
PENTAGON
WASHINGTON DC
20310-0103

1 HQDA
SARD TR R MORRISON
PENTAGON
WASHINGTON DC
20310-0103

1 CHAIRMAN DOD EXPLOSIVES
SAFETY BD
HOFFMAN BLDG 1 RM 856 C
2461 EISENHOWER AVE
ALEXANDRIA VA 22331-0001

1 HQS US ARMY MATERIEL CMD
AMCICP AD M FISETTTE
5001 EISENHOWER AVE
ALEXANDRIA VA 22331-0001

1 US ARMY BMDS CMD
ADVANCED TECHLGY CTR
PO BOX 1500
HUNTSVILLE AL 35807-3801

1 OFC OF THE PRODUCT MGR
SFAE AR HIP IP
R DE KLEINE
155MM HOWITZER M109A6
PALADIN
PICATINNY ARSENAL NJ
07806-5000

1 PM ADV FIELD ARTLRY SYS
SFAE ASM AF E
J SHIELDS
PICATINNY ARSENAL NJ
07801-5000

1 PM ADV FIELD ARTLRY SYS
SFAE ASM AF Q W WARREN
PICATINNY ARSENAL NJ
07801-5000

NO. OF
COPIES ORGANIZATION

1 CDR US ARMY ARDEC
PROD BASE MODERNIZATION AGENCY
AMSMC PBM A SIKLOSI
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
PROD BASE MODRNZTN AGENCY
AMSMC PBM E L LAIBSON
PICATINNY ARSENAL NJ
07806-5000

1 PM PEO ARMAMENTS
TANK MAIN ARMAMENT SYS
AMCPM TMA
PICATINNY ARSENAL NJ
07806-5000

1 PM PEO ARMAMENTS
TANK MAIN ARMAMENT SYS
AMCPM TMA 105
PICATINNY ARSENAL NJ
07806-5000

1 PM PEO ARMAMENTS
TANK MAIN ARMAMENT SYS
AMCPM TMA AS H YUEN
PICATINNY ARSENAL NJ
07806-5000

2 CDR US ARMY ARDEC
AMSTA AR CCH V
C MANDALA
E FENNELL
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
AMSTA AR CCS
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
AMSTA AR AEE
J LANNON
PICATINNY ARSENAL NJ
07806-5000

NO. OF
COPIES ORGANIZATION

10 CDR US ARMY ARDEC
AMSTA AR AEE B
D DOWNS
S EINSTEIN
S WESTLEY
S BERNSTEIN
J RUTKOWSKI
B BRODMAN
P O'REILLY
R CIRINCIONE
P HUI
J O'REILLY
PICATINNY ARSENAL NJ
07806-5000

5 CDR US ARMY ARDEC
AMSTA AR AEE WW
M MEZGER
J PINTO
D WIEGAND
P LU
C CHU
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
AMSTA AR AES
S KAPLOWITZ
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
AMSTA AR FSA T
M SALSURY
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
AMSTA AR FSC
G FERDINAND
PICATINNY ARSENAL NJ
07806-5000

1 COMMANDER
AMSTA AR FS
T GORA
PICATINNY ARSENAL NJ
07806-5000

NO. OF
COPIES ORGANIZATION

1 CDR US ARMY ARDEC
AMSTA AR FS DH
J FENECK
PICATINNY ARSENAL NJ
07806-5000

3 CDR US ARMY ARDEC
AMSTA AR FSS A
R KOPMANN
B MACHAK
L PINDER
PICATINNY ARSENAL NJ
07806-5000

1 CDR US ARMY ARDEC
AMSTA AR FSN N
K CHUNG
PICATINNY ARSENAL NJ
07806-5000

1 DIR BENET WEAPONS LAB
AMSTA AR CCB RA
G A PFLEGL
WATERVLIET NY 12189-4050

1 DIR BENET WEAPONS LAB
AMSTA AR CCB RT
S SOPOK
WATERVLIET NY 12189-4050

1 DIR BENET WEAPONS LAB
AMSTA AR CCB S
R FISCELLA
WATERVLIET NY 12189-4050

2 CDR US ARMY RSRCH OFC
TECH LIB
D MANN
PO BOX 12211
RESEARCH TRIANGLE PARK NC
27709-2211

1 CDR USACECOM
R&D TECH LIB
ASQNC ELC IS L R
MYER CTR
FT MONMOUTH NJ
07703-5301

NO. OF
COPIES ORGANIZATION

1 CMDT USA AVIATION SCHL
AVIATION AGENCY
FT RUCKER AL 36360

1 PM US ARMY TANK AUTOMTVE CMD
AMCPM ABMS T DEAN
WARREN MI 48092-2498

1 PM US ARMY TANK AUTOMTVE CMD
FIGHTING VEHICLE SYSTEMS
SFAE ASM BV
WARREN MI 48397-5000

1 PM ABRAMS TANK SYSTEM
SFAE ASM AB
WARREN MI 48397-5000

1 DIR HQ TRAC RPD
ATCD MA
FT MONROE VA 23651-5143

1 COMMANDER
US ARMY BELVOIR R&D CTR
STRBE WC
FT BELVOIR VA 22060-5006

1 COMMANDANT
US ARMY CMD & GEN
STAFF COLLEGE
FT LEAVENWORTH KS 66027

1 COMMANDANT
USA SPECIAL WARFARE SCHL
REV AND TRNG LIT DIV
FT BRAGG NC 28307

1 COMMANDER
RADFORD ARMY
AMMUNITION PLANT
SMCAR QA HI LIB
RADFORD VA 24141-0298

1 COMMANDER
US ARMY NGIC
AMXST MC 3
220 SEVENTH ST NE
CHARLOTTESVILLE VA
22901-5396

NO. OF
COPIES ORGANIZATION

1 COMMANDANT
USAFAC&S
ATSF CD COL T STRICKLIN
FT SILL OK 73503-5600

1 COMMANDANT
USAF&S
ATSF CN P GROSS
FT SILL OK 73503-5600

1 CMDT USA ARMOR SCHL
ARMOR AGENCY
ATZK CD MS
M FALKOVITICH
FT KNOX KY 40121-5215

2 CDR NAVAL SEA SYSTEMS CMD
SEA 62R
SEA 64
WASHINGTON DC
20362-5101

1 CDR NAVAL AIR SYSTEMS CMD
AIR 954 TECH LIBRARY
WASHINGTON DC 20360

4 CDR NAVAL RSRCH LAB
TECH LIBRARY
CODE 4410
K KAILASANATE
J BORIS
E ORAN
WASHINGTON DC
20375-5000

1 OFFICE OF NAVAL RSRCH
CODE 473 R S MILLER
800 N QUINCY ST
ARLINGTON VA 22217-9999

1 OFFICE OF NAVAL TECHLGY
ONT 213 D SIEGEL
800 N QUINCY ST
ARLINGTON VA 22217-5000

1 CDR NAVAL SURFACE WARFARE
CTR
CODE 730
SILVER SPRING MD 20903-5000

NO. OF
COPIES ORGANIZATION

7 CDR NAVAL SURFACE WARFARE
CTR
T C SMITH
K RICE
S MITCHELL
S PETERS
J CONSAGA
C GOTZMER
TECH LIB
INDIAN HEAD MD 20640-5000

1 CDR NAVAL SURFACE WARFARE
CTR
CODE G30 GUNS & MUNITIONS DIV
DAHLGREN VA 22448-5000

1 CDR NAVAL SURFACE WARFARE
CTR
CODE G32
GUNS SYSTEMS DIV
DAHLGREN VA 22448-5000

1 CDR NAVAL SURFACE WARFARE
CTR
CODE E23
TECH LIB
DAHLGREN VA 22448-5000

2 CDR NAVAL AIR WARFARE CTR
CODE 388
C F PRICE
T BOGGS
CHINA LAKE CA 93555-6001

2 CDR NAVAL AIR WARFARE CTR
CODE 3895
T PARR
R DERR
CHINA LAKE CA 93555-6001

1 CDR NAVAL AIR WARFARE CTR
INFORMATION SCIENCE DIV
CHINA LAKE CA 93555-6001

1 COMMANDER OFFICER
CODE 5B331 TECH LIB
NAVAL UNDERWATER SYS CTR
NEWPORT RI 02840

NO. OF
COPIES ORGANIZATION

1 AFOSR NA
J TISHKOFF
BOLLING AFB DC 20332-6448

1 OLAC PL TSTL
D SHIPLETT
EDWARDS AFB CA 93523-5000

3 AL LSCF
J LEVINE
L QUINN
T EDWARDS
EDWARDS AFB CA 93523-5000

1 WL MNAA
B SIMPSON
EGLIN AFB FL 32542-5434

1 WL MNME
ENERGETIC MATERIALS BR
2306 PERIMETER RD
STE 9
EGLIN AFB FL 32542-5910

1 WL MNSH
R DRABEZUK
EGLIN AFB FL 32542-5434

2 NASA LANGLEY RSRCH CTR
M S 408
W SCALLION
D WITCOFSKI
HAMPTON VA 23605

1 CIA
OFC OF THE CTR REFERENCES
DISSEMINATION BR
RM GE 47 HQS
WASHINGTON DC 20502

1 CIA
J BACKOFEN
NHB RM 5N01
WASHINGTON DC 20505

1 SDIO TNI
L H CAVENY
PENTAGON
WASHINGTON DC 20301-7100

NO. OF
COPIES ORGANIZATION

1 SDIO DA
E GERRY
PENTAGON
WASHINGTON DC 21301-7100

2 HQ DNA
D LEWIS
A FAHEY
6801 TELEGRAPH RD
ALEXANDRIA VA 22310-3398

1 DIR SANDIA NATL LABS
M BAER DEPT 1512
PO BOX 5800
ALBUQUERQUE NM 87185

1 DIR SANDIA NATL LABS
R CARLING
COMBUSTION RSRCH FACILITY
LIVERMORE CA 94551-0469

2 DIR LLNL
L 355
A BUKINGHAM
M FINGER
PO BOX 808
LIVERMORE CA 94550-0622

1 DIR LANL
T3 D BUTLER
PO BOX 1663
LOS ALAMOS NM 87544

2 BATTELLE
TWSTIAC
V LEVIN
505 KING AVE
COLUMBUS OH 43201-2693

1 BATELLE PNL
M GARNICH
PO BOX 999
RICHLAND WA 99352

1 THE UNIV OF AUSTIN TEXAS
INST FOR ADVNCD TECHLGY
T M KIEHNE
4030 D W BRAKER LANE
AUSTIN TX 78759-5329

NO. OF
COPIES ORGANIZATION

2 CPI JHU
H J HOFFMAN
T CHRISTIAN
10630 LITTLE PATUXENT PKWY
STE 202
COLUMBIA MD 21044-3200

1 AFELM THE RAND CORP
LIBRARY D
1700 MAIN ST
SANTA MONICA CA 90401-3297

1 BRIGHAM YOUNG UNIV
M BECKSTEAD
DEPT OF CHEMICAL ENGRG
PROVO UT 84601

1 CALIF INSTITUTE OF TECHLGY
L D STRAND MS 125 224
JET PROPULSION LAB
4800 OAK GROVE DR
PASADENA CA 91109

1 CALIF INSTITUTE OF TECHLGY
F E C CULICK
204 KARMAN LAB
MAIL STOP 301 46
1201 E CALIFORNIA STR
PASADENA CA 91109

1 MILLERSVILLE UNIV
PHYSICS DEPT
C W PRICE
MILLERSVILLE PA 17551

3 GEORGIA INSTITUTE OF TECHLGY
SCHOOL OF AEROSPACE ENGRG
B T ZIM
E PRICE
W C STRAHLE
ATLANTA GA 30332

2 UNIV OF ILLINOIS
DEPT OF MECH INDUSTRY ENGRG
H KRIER
R BEDDINI
144 MEB 1206 N GREEN ST
URBANA IL 61801-2978

NO. OF
COPIES ORGANIZATION

1 UNIV OF MASSACHUSETTS
DEPT OF MECHANICAL ENGRG
K JAKUS
AMHERST MA 01002-0014

1 UNIV OF MINNESOTA
DEPT OF MECHANICAL ENERG
E FLETCHER
MINNEAPOLIS MN 55414-3368

4 PENNSYLVANIA STATE UNIV
DEPT OF MECHANICAL ENGRG
V YANG
K KUO
S THYNELL
G SETTLES
UNIVERSITY PARK PA 16802-7501

1 RENSSELAER POLYTECH INST
DEPT OF MATHEMATICS
TROY NY 12181

1 RUTGERS UNIVERSITY
DEPT OF MECH AND AERO ENGRG
S TEMKIN
UNIV HEIGHTS CAMPUS
NEW BRUNSWICK NJ 08903

1 UNIV OF UTAH
DEPT OF CHEMICAL ENGRG
A BAER
SALT LAKE CITY UT 84112-1194

1 WASHINGTON STATE UNIV
DEPT OF MECHANICAL ENGRG
C T CROWE
PULLMAN WA 99163-5201

1 ARROW TECH ASSOC INC
1233 SHELBURNE RD D-8
SOUTH BURLINGTON VT 05403

2 AAI CORPORATION
J FRANKLE
D CLEVELAND
PO BOX 126
HUNTVALLEY MD 21030-0126

NO. OF
COPIES ORGANIZATION

8 ALLIANT TECHSYSTEMS INC
R E TOMPKINS
J KENNEDY
J BODE
C CANDLAND
L OSGOOD
R BURETTA
R BECKER
M SWENSON
600 SECOND ST NE
HOPKINS MN 55343

1 ELI FREEDMAN AND ASSOC
E FREEDMAN
2411 DIANA RD
BALTIMORE MD 21209-1525

1 GENERAL APPLIED SCIENCES LAB
J ERDOS
77 RAYNOR AVE
RONKONKAMA NY 11779-6649

1 G D DEFENSE SYSTEMS
TACTICAL SYSTEM DEPT
J MANDZY
100 PLASTICS AVE
PITTSFIELD MA 01201-3698

1 ITTRI
M J KLEIN
10 W 35TH ST
CHICAGO IL 60616-3799

6 ALLIANT TECHSYSTEMS
L GIZZI
D A WORRELL
W J WORRELL
C CHANDLER
S RITCHIE
H ZEIGLER
RADFORD ARMY AMMO PLANT
RADFORD VA 24141-0299

2 ALLIANT TECHSYSTEMS
W B WALKUP
T F FARABAUGH
ALLEGHENY BALLISTICS LAB
PO BOX 210
ROCKET CENTER WV 26726

NO. OF
COPIES ORGANIZATION

1 ALLIANT TECHSYSTEMS
R CARTWRIGHT
AEROSPACE
100 HOWARD BLVD
KENVILLE NJ 07847

1 ALLIANT TECHSYSTEMS
B M RIGGLEMAN
HERCULES PLAZA
WILMINGTON DE 19894

1 MARTIN MARIETTA ARM SYS
J TALLEY RM 1309
LAKESIDE AVE
BURLINGTON VT 05401

1 MBR RESEARCH INC
DR MOSHE BEN REUVEN
601 EWING STE C 22
PRINCETON NJ 08540

1 PRIMEX
F E WOLF
BADGER ARMY AMMO PLANT
BARABOO WI 53913

3 PRIMEX
E J KIRSCHKE
A F GONZALEZ
J DRUMMOND
D W WORTHINGTON
PO BOX 222
SAINT MARKS FL 32355-0222

2 PRIMEX
N HYLTON
J BUZZETT
10101 9TH ST NORTH
ST PETERSBURG FL 33716

1 PAUL GOUGH ASSOC INC
P S GOUGH
1048 SOUTH ST
PORTSMOUTH NH 03801-5423

1 PHYSICS INTRNATNL LIB
H WAYNE WAMPLER
PO BOX 5010
SAN LEANDRO CA 94577-0599

NO. OF
COPIES ORGANIZATION

1 FRELIN ASSOCIATES INC
4411 QUAKER HILLS CT
HAVRE DE GRACE MD 21078

1 PRINCETON COMBUSTION
RESEARCH LABS INC
N MESSINA
PRINCETON CORPORATE PLAZA
11 DEERPARK DR BLDG IV STE 119
MONMOUTH JUNCTION NJ 08852

2 ROCKWELL INTRNTNL SCIENCE CTR
DR S CHAKRAVARTHY
DR S PALANISWAMY
1049 CAMINO DOS RIOS
PO BOX 1085
THOUSAND OAKS CA 91360

1 SAIC
M PALMER
2109 AIR PARK RD
ALBUQUERQUE NM 87106

1 SOUTHWEST RSRCH INST
J P RIEGEL
6220 CULEBRA RD
PO DRAWER 28510
SAN ANTONIO TX 78228-0510

1 SVERDRUP TECHLGY INC
DR JOHN DUER
2001 AEROSPACE PKWY
BROOK PARK OH 44142

3 THIOKOL CORP
R WILLER
R BIDDLE
TECH LIB
ELKTON DIV
PO BOX 241
ELKTON D 21921-0241

3 VERITAY TECHGY INC
E FISHER
R SALIZONI
J BARNES
4845 MILLERSPORT HWY
EAST AMHERST NY 14501-0305

NO. OF
COPIES ORGANIZATION

NO. OF
COPIES ORGANIZATION

1 PRIMEX
E STEINER
DIR LARGE CAL R & D
PO BOX 127
RED LION PA 17356

1 UNIVERSAL PROPULSION CO
H J MCSPADDEN
25401 NORTH CENTRAL AVE
PHOENIX AZ 85027-7837

1 SRI INTERNATIONAL
TECH LIB
PROPULSION SCIENCES DIV
333 RAVENWOOD AVE
MENLO PARK CA 94025-3493

ABERDEEN PROVING GROUND

1 CDR USAATC
STECs LI R HENDRICKSEN

35 DIR USARL
AMSRL WM B A HORST
AMSRL WM BE
T MINOR
T COFFEE
G WREN
A BIRK
J DE SPIRITO
C LEVERITT
W OBERLE
K WHITE
L M CHANG
J COLBURN
P CONROY
D KOOKER
M NUSCA
AMSRL WM BC
P PLOSTINS
M BUNDY
B GUIDOS
D LYON
J GARNER
V OSKAY
J SAHU
P WEINACHT
H EDGE

AMSRL WM BD
B FORCH
A JUHASZ
B RICE
C CHABALOWSKI
AMSRL WM MC
J BEATTY
R ADLER
G KRASKO
J MONTGOMERY
AMSRL WM MB
B BURNS
L BURTON
AMSRL CI HA
W STUREK
AMSRL CI
C NIETUBICZ

INTENTIONALLY LEFT BLANK.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
<small>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.</small>				
1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE June 1999	3. REPORT TYPE AND DATES COVERED Final, Jul 97 - Dec 97		
4. TITLE AND SUBTITLE Parametric Erosion Investigation (Propellant Adiabatic Flame Temperature)		5. FUNDING NUMBERS IL1622105AH84		
6. AUTHOR(S) Paul J. Conroy, Paul Weinacht, and Michael J. Nusca				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army Research Laboratory ATTN: AMSRL-WM-BE Aberdeen Proving Ground, MD 21005-5066		8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TR-1954		
9. SPONSORING/MONITORING AGENCY NAMES(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER		
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.		12b. DISTRIBUTION CODE		
13. ABSTRACT (Maximum 200 words) In this report, we investigate the influence of quasi-independent parameters and their potential influence on erosion in guns. Specifically, we examine the effects of flame temperature and the effect of assuming that the Lewis Number (ratio of mass to heat transport to the surface), Le , is one. The adiabatic flame temperature was reduced for a propellant through the addition of a diluent from a high of 3,843 K similar to that of M9 down to 3,004 K, which is near the value for M30A1 propellant. Also shown are mass fractions of critical species at the surface with and without the assumption of $Le = 1$, demonstrating that certain species preferentially reach the surface providing varied conditions for the surface reactions. The results for gun tube bore surface regression qualitatively agree with previous studies and with current experimental data. The propellant composition influence upon erosion must still be inferred at this time from the presence of specific product species at the surface because the finite-rate gas surface reactions are not well known under ballistic conditions.				
14. SUBJECT TERMS erosion, heat transfer, adiabatic flame temperature		15. NUMBER OF PAGES 31		
		16. PRICE CODE		
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

INTENTIONALLY LEFT BLANK.

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. ARL Report Number/Author ARL-TR-1954 (Conroy) Date of Report June 1999
2. Date Report Received _____
3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. Specifically, how is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided, or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT
ADDRESS

Organization

Name

E-mail Name

Street or P.O. Box No.

City, State, Zip Code

7. If indicating a Change of Address or Address Correction, please provide the Current or Correct address above and the Old or Incorrect address below.

OLD
ADDRESS

Organization

Name

Street or P.O. Box No.

City, State, Zip Code

(Remove this sheet, fold as indicated, tape closed, and mail.)
(DO NOT STAPLE)